


SPECIAL DENSE CONVENTIONAL CASTABLES

LICOFEST



BÉTONS CONVENTIONNELS DENSES SPÉCIAUX



Every product listed in this section offers at least one special additional feature and/or property that "makes the difference" compared to traditional castables.

Tous les produits de ce groupe sont formulés pour offrir des caractéristiques supplémentaires en conditions de marche particulières.

ALUMINA BASED

Cr₂O₃ BASED

PRODUCT	T max.	Chem. analysis		BD kg/m ³ at 815° C.	Setting	CCS		TC W/mK at 800° C.	Installation
	°C	Al ₂ O ₃	Fe ₂ O ₃			°C	N/mm ²		
LICOFEST 1200 AL	1200	39	16	2650	H	105 1100	92 36	1,82	C - V
LICOFEST 18 HT	1350	44	3	1990	H	105 1300	40 30	0,63	C - V
LICOFEST 28 HT	1500	52	0,9	2050	H	105 1500	38 42	0,74	C - V
LICOFEST 37/4	1550	79	4,6	2400	H	105 1500	50 40	0,90	C - V
LICOFEST 1600 0-10 QH	1600	66	0,8	2400	H	105 1500	50 50	1	C - V
LICOFEST 36 AN	1600	66	0,8	2320	H	105 1500	50 60	1	C - V
LICOFEST 40 CB	1600	72	0,3	2350	H	105 1500	55 80	1,23	C - V
LICOFEST H 82	1700	86	1	2650	H	105 1500	50 50	1,60	C - V
LICOFEST KRB 94	1730	93	0,8	2700	H	105 1500	60 60	1,60	C - V
LICOFEST KOR 94	1730	94	0,4	2960	H	105 1500	81 130	2,20	C - V
LICOFEST TAL 96 K	1740	94	0,4	2700	H	105 1500	70 62	1,60	C - V
LICOFEST H 95	1750	95	0,1	2790	H	105 1500	70 65	2,25	C - V
LICOFEST ALTA	1800	95	0,08	2900	H	105 1500	80 80	2,31	C - V
LICOFEST CR	1460	33 (Cr ₂ O ₃)	13	2700	H	105 1300	40 40	1,35	C - V

Produits aux usines de Levate (I) et Bexbach (D)

Binding key: **H** = Hydraulic

Légende prise: **H** = Hydraulique

Installation system key: **C** = Casting, pouring
V = Vibration

Légende installation: **C** = Coulage
V = Vibration